



PRODUCTS YOU CAN TRUSS

MSR - Southern Yellow Pine

Name	Species	Grade	Size	Bending (Fb)	Tension Parallel (Ft)	Shear Parallel (Fv)	Compression Perpendicular (Fc \perp)	Compression Parallel (Fc)	Modulus of Elasticity (E)	Modulus of Elasticity (Emin)	Specific Gravity
SYP MSR 1650f-1.7E	SYP	MSR 1650	Machine	1,650	1,020	175	565	1750	1,700,000	860,000	0.55
SYP MSR 2250f-1.9E	SYP	MSR 2250	Machine	2,250	1,750	190	805	1925	1,900,000	970,000	0.57
SYP MSR 2400f-2.0E	SYP	MSR 2400	Machine	2,400	1,925	190	805	1975	2,000,000	1,020,000	0.57
SYP MSR 2700f-2.2E	SYP	MSR 2700	Machine	2,700	2,150	190	805	2100	2,200,000	1,120,000	0.57